


SNC70-HXP Form-In-Place

A rapid cure, nickel-coated graphite-filled silicone elastomer Form-In-Place gasket material.

Laird Technologies introduces another product in the EMI Sentry family. These Form-In-Place pastes are extremely fast curing with reliable shielding effectiveness and strength

Laird Technologies' Form-In-Place is an automated system for dispensing conductive elastomer EMI shielding and grounding gaskets onto metal or plastic substrates. This product is particularly ideal for base stations, PDAs, PC cards, radios, mobile phones, as well as many other cast enclosures and packaged electronic assemblies.



* does not represent actual color

TYPICAL VALUES

	TEST METHOD	UNITS	SNC70-HXP
Elastomer			Silicone
Filler			Nickel/Graphite
ELECTRICAL PROPERTIES			
Volume Resistivity		ohm-cm	0.030
Shielding Effectiveness	MIL-DTL-83528C		
200 MHz to 10 GHz	Para. 4.5.12	dB	>90
PHYSICAL PROPERTIES			
Hardness	ASTM D2240	Shore A	70
Density (cured)	ASTM D792	g/cm ³	2.5
Density (uncured)	LT-FIP-CLE-09	g/cm ³	2.3
Compression Set	ASTM D395	%	15
Adhesion Strength (Al)	LT-FIP-CLE-03	N/cm ²	>180
Compression-Deflection (a)	LT-FIP-CLE-07		
at 20% compression		lb/in	3.2
at 40% compression		lb/in	11.5
Temperature Range		°C	-50°C to 150°C
UL rating	UL-94		V0
CURING REQUIREMENTS			
Cure conditions		120°C minimum	
Cure Time at 125°C (b)	LT-FIP-CLE-14		1 hour

- (a) Compression-deflection bead size 0.60 mm (H) x 0.70 mm (W) rev. 07/02/09
- (b) Time to effectively cure a bead will necessarily depend on individual conditions, including but not limited to bead size, shield size and weight, oven capacity, and oven ramp-rates.

Americas: +1 866.928.8181
Europe: +49 8031.2460.0
Asia: +86 755.2714.1166



EMI-DS-FIP-SNC70-HXP 0113

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. Responsibility for the use and application of Laird Technologies materials rests with the end user, since Laird Technologies and its agents cannot be aware of all potential uses. Laird Technologies makes no warranties as to the fitness, merchantability or suitability of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2012 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trade marks or registered trade marks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights.